



Flexible Moulding Installation Tips

Fastening

For best results, the use of construction type adhesive in addition to pneumatic pin nailing to wall or ceiling abutments, Mitre Bond instant adhesive on all end joints, is recommended. Use of tape or clamps may be helpful in securing material in position while adhesives bond. Nails should be kept to a minimum 3/8" from any edge.

Cutting

Material can be cut, shaped and sanded using standard woodworking equipment. Note that the wood grain on stain grade material is only on the surface and will be eliminated if sanded.

Stain

The use of water base stain such as Minwax work wells and is recommended. Apply with brush or rag and wipe off. Additional coats may be applied if necessary to match wood. Be sure to allow first coat to dry completely before applying more stain. Finish with clear coat after staining.

Paint

All paints work well but latex is recommended. Primer is not necessary but best results are seen when a primer coat is applied. When using Alkyd Enamels or Oil based Enamels a water base or Latex undercoat is required. Never paint before installation. The material is flexible and the paint may crack during installation.